

# Data Sheet

## Fortis LL

Suggested print sets	unit	value	test method
extruder temp	C°	250-0+15	internal
plate temp	C°	90	internal
min. nozzle diameter	mm.	0.2	internal
fun	%	20-100	internal
print speed	mm/1°	40-60	internal
<b>Property</b>			
Density	g/cm3	0.62	ISO 1183
HDT	C°	62	ISO 75B-1
Vicat softening temp.	C°	110	ISO 306
Flexural modulus	MPa	990	ISO 178

## Disclaimer

The above information is provide in good fact .Treedfilaments is not responsible for any processing which may occur to product finished articles , packaging materials and other . Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .