



SUGGESTED PRINT SETS (1)			
Suggested print sets	unit	value	test method
extruder temp	C°	235-250	internal
plate temp	C°	90	internal
min. nozzle diameter	mm.	0,2	internal
fan	%	0-70	internal
print speed	mm/l°	30-60	internal
PROPERTY			
Physical			
Specific gravity	g/cm3	1.06	ISO 1183
Mechanical			
Tensile strength yield	MPa	46	ISO 527
Tensile strength break	MPa	34	ISO 527
Tensile elongation	%	31	ISO 527
Charpy impact (23°C)	kJ/m ²	20	ISO 179
Charpy impact (-30°C)	kJ/m ²	10	ISO 179
Flexural strenght	MPa	76	ISO 178
Flexural modulus	GPa	2.2	ISO 178
Izod impact strength (23°C)	kJ/m ²	19	ISO 180/1A
Izod impact strength (-30°C)	kJ/m ²	9	ISO 180/1A
Thermal			
Heat distortion temp. (unannealed)	°C	83	ISO 75 A
Heat distortion temp. (annealed)	°C	98	ISO 75 A
Coefficient of linear thermal expansion	-	8.6 x 10 ⁻⁵	ISO 11359
Flammability	-	1.5 mm HB	UL 94
Mold shrinkage	%	0.4-0.7	ISO 294-4
Vicat softening temp.	°C	104	ISO 306

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsible for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .



ADDITIONAL INFORMATIONS

In General filaments made with ABS MED can be processed on conventional 3D printer using FDM / FFF technology.

ABS MED is a special ABS developed for 3D printing and to obtain best results we recommend pre drying the filaments at 70° for 2 h. Increase drying time for spools up 1 kg.

Don't leave the filament stopped inside the nozzle more than 20 min. If that down the temperature under 210°, better stop the thermal control.

(1) Suggested print set merely represent a recommendation for general use . Every printer necessity a specific set , nozzle temp, bed temp, etc .

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsible for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .

CONTAIN NO FOLLOWING SUBSTANCES

1. Halogen (F, Br, I) and its compound
2. Halogen (C1)
3. PBDEs (polybrominated biphenyl ethers)
4. PBBs (polybrominated biphenyls)
5. Ozone depleting chemicals (CFCs & HCFCs)
6. Chlorinated paraffin (C10-C13)
7. Polyvinyl chloride (PVC)
8. Mercury (Hg) and its compounds
9. Lead (Pb) and its compounds
10. Cadmium (Cd) and its compounds
11. Chromium (Cr) and its compounds
12. Arsenic (As) and its compounds
13. Antimony (Sb) and its compounds
14. Selenium (Se) and its compounds
15. Barium (Ba) and its compounds
16. Beryllium (Be) and its compounds
17. Bismuth (Bi) and its compounds
18. Organic tin compounds (TBT, TPT, DOT, DBT)
19. Poly naphthalenes
20. Asbestos
21. Phthalates
22. 2-(2'-hydroxy-3', 5'-di-tert-butylphenyl) benzotriazole
23. PFOA, PFOS
24. Bisphenol A
25. Formaldehyde
26. Dimethylfumarate (DMF)
27. Triclosan
28. Nickel
29. REACH - candidate list of SVHC
30. Radioactive substances
31. Natural latex
32. Dioxina and furans
33. Primary aromatic amines (PAA)
34. Perchlorate
35. Hexachlorobenzene
36. Mirex
37. Specified amine compounds
38. Benzene
39. Polyamide
40. PVDC (polyvinylidene chloride)
41. ESBO (expoxidized soybean oil)
42. Formamide
43. Hexabromocyclododecane (HBCDD)
44. Red phosphorus
45. Aniline - formaldehyde polycondensate
46. Fluorescent powder
47. 4,4' - Sulfonyldiphenol (BPS)
48. Diisononyl phthalate (DINP)
49. Di-isodecyl phthalate (DIDP)
50. Di-n-octyl phthalate (DnOP)
51. Diethyl phthalate (DEP)
52. Dimethyl phthalate (DMP)
53. Cobalt
54. Mica
55. Graphite
56. Manganese (Mn) and its compounds
57. Tri-o-cresyl phosphate
58. Tris (2-cchloroethyl)phosphate(TCEP)
59. Tris (aziridiny) phosphate
60. Tris (2,3-dibromopropyl) phosphate

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsible for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .



61. Tris (1-chloro-2-propyl) phosphate (TCPP)
62. Tris (1,3-dichloro-2-propyl) phosphate (TDCPP)
63. Perfluorohexane-1-sulphonic acid and its salts (PFHxS)
64. Benzenamine, N-phenyl-, reaction products with styrene and 2,4,4-trimethylpentene (BNST)
65. Polychlorinated biphenyls (PCBs) and terphenyls (PCTs) and naphthalenes (PCNs)
66. Azo colorants (according to REACH-ANNEX-XVII-APPENDIX 8)
67. APEO: including alkyl phenol (AP), octylphenol (OP), Nonylphenol (NP), octylphenol ethoxylates (OPE), nonylphenol ethoxylates (NPE)

With regard to composition of above grades of products, the aforesaid products, comply with the Directives of RoHS (2011/65/EU), 2003/11/EC

Recommended applications

Home care	Yes
Medical devices	Yes
Medical supplies	Yes
Assistive devices	Yes

Certifications

USP<88> class VI

For more technical infos, please contact us : team@treedfilaments.com

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsible for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .